















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	Tumbled, Natural Course Heights; 2:1 Random Ashlar
	PATTERN	Random Ashlar
	HEIGHTS	4"-12" random (Full Bed & Thin Veneer)
	LENGTHS	Full Bed-Depth: 8"-30" Thin Veneer: 6" - 20" (Crated or Palletized Material Can Exceed 20")
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer
	COLORS	Buff, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton Available in Thin Veneer
	WEIGHT	14 lbs per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f Pallet
	NOTES	Tumbled "Fond du Lac Manor" Crated material can exceed 20 inches.

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101