















## SPECIFICATIONS

	<b>GEOLOGY</b>	Sandstone
	<b>TYPE</b>	100% bedface
	<b>PATTERN</b>	2:1 random ashlar
	<b>HEIGHTS</b>	4"-10"
	<b>LENGTHS</b>	6" - 20" (Crated or palletized material can exceed 20")
	<b>DEPTHS</b>	3/4" to 1-1/4"
	<b>COLORS</b>	Beige, Black, Brown, Buff, Charcoal, Gray-Grey, Tan
	<b>COVERAGE</b>	35-40 sq ft per ton (Full Bed-Depth)
	<b>WEIGHT</b>	13 lbs per square foot
	<b>FLATS</b>	10 s/f Box, 100 s/f Crate, 180 s/f Crate
	<b>CORNERS</b>	10 ln/ft Box, 100 ln/ft Crate
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	2.7
Bulk Specific Gravity	2.33

### ASTM C-170

Parallel to Rift, Dry (psi)	12000
Parallel to Rift, Wet (psi)	
Perpendicular to Rift, Dry (psi)	17100
Perpendicular to Rift, Wet (psi)	

### ASTM C-99

Parallel to Rift, Dry (psi)	2939
Parallel to Rift, Wet (psi)	

### ASTM C-880

Perpendicular to Rift, Dry (psi)	2041
Perpendicular to Rift, Wet (psi)	



**GOLD QUARRIER**  
ANSI/NSC 573-2013  
C0290908-101



**GOLD FABRICATOR**  
ANSI/NSC 573-2013  
C0289215-101