















SPECIFICATIONS

| | | |
|--|-----------------|---|
|  | GEOLOGY | Limestone |
|  | TYPE | 100% Bedface |
|  | PATTERN | Natural Course Heights 2:1 Random Ashlar |
|  | HEIGHTS | 4" - 12" random (Full Bed & Thin Veneer) |
|  | LENGTHS | Full Bed: 8"-30" Thin Veneer: 6" - 20" (Crated or Palletized material can exceed 20") |
|  | DEPTHS | 3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer |
|  | COLORS | Beige, Buff, Gray-Grey |
|  | COVERAGE | Full Bed Depth Veneer: 35-40 Square Feet Per Ton |
|  | WEIGHT | 14.9 lbs. per square foot (Thin Veneer) |
|  | FLATS | 10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet |
|  | CORNERS | 10 l/f Box; 100 l/f Crate; 100 l/f pallet |
|  | NOTES | |

ASTM C-97

| | |
|-----------------------|------|
| Water Absorption % | .31 |
| Bulk Specific Gravity | 2.83 |

ASTM C-170

| | |
|----------------------------------|-------|
| Parallel to Rift, Dry (psi) | 36100 |
| Parallel to Rift, Wet (psi) | 32000 |
| Perpendicular to Rift, Dry (psi) | 35800 |
| Perpendicular to Rift, Wet (psi) | 30000 |

ASTM C-99

| | |
|-----------------------------|------|
| Parallel to Rift, Dry (psi) | 3770 |
| Parallel to Rift, Wet (psi) | 3500 |

ASTM C-880

| | |
|----------------------------------|------|
| Perpendicular to Rift, Dry (psi) | 1780 |
| Perpendicular to Rift, Wet (psi) | 1730 |



GOLD QUARRIER
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101