















## SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Bedface
	PATTERN	Natural Course Heights   2:1 Random Ashlar
	HEIGHTS	4" - 12" (Full Bed & Thin Veneer)
	LENGTHS	8"-30" (Full Bed), 8"-24" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	3/4" to 1-1/4" (Thin Veneer)
	COLORS	Beige, Brown, Buff, Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet/Ton
	WEIGHT	14.2 lbs. per square foot.
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Also previously known as the legacy NSVI product, " <b>Bradford</b> ". Some photos may still have the former product name.

### ASTM C-97

Water Absorption %	.50 psi
Bulk Specific Gravity	2.79 psi

### ASTM C-170

Parallel to Rift, Dry	21300 psi
Parallel to Rift, Wet	20300 psi
Perpendicular to Rift, Dry	29400 psi
Perpendicular to Rift, Wet	29100 psi

### ASTM C-99

Parallel to Rift, Dry	2040 psi
Parallel to Rift, Wet	1690 psi

### ASTM C-880

Perpendicular to Rift, Dry	
Perpendicular to Rift, Wet	



**GOLD QUARRIER**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101