















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	Natural Course Heights 100% Split Face
	PATTERN	2:1 Random Ashlar
	HEIGHTS	Varies from 2"-9" (Full Bed); 2"-6" (Thin Veneer)
	LENGTHS	Full Veneer: 8" - 36" Thin Veneer: 6" - 20" (Crated or palletized material can exceed 20")
	DEPTHS	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Beige , Buff , Charcoal , Gray - Grey , Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 sq ft per ton
	WEIGHT	14.9 lbs per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Formerly known as NSVI's "Luxemburg"; pre-packaged blend of 50% <i>Fond du Lac Country</i> , and 50% <i>Graphite Country</i> .

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36000
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRY
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101