















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed & Thin Veneer)
	LENGTHS	Full Veneer: 8"-36" Thin Veneer: 6" - 20" (Crated/palletized material can exceed 20")
	DEPTHS	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Beige, Buff, Gray-Grey, Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14.9 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box, 100 s/f Crate or Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate or Pallet
	NOTES	This was also known as the legacy NSVI product, " Fairmont ". Some photos could show the former NSVI product name.

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730

