














SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed); 2"-9" (Thin Veneer)
	LENGTHS	Random, 8"-36" (Full Bed); 6" - 20" (Thin Veneer; crated/palletized material can exceed 20")
	DEPTH	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Buff , Cream , Gray - Grey , Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton Also Available in Thin Veneer
	WEIGHT	14 pounds per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f Pallet
	NOTES	

ASTM C-97

Water Absorption %	1.60
Bulk Specific Gravity	2.54

ASTM C-170

Parallel to Rift, Dry (psi)	15100
Parallel to Rift, Wet (psi)	13200
Perpendicular to Rift, Dry (psi)	15100
Perpendicular to Rift, Wet (psi)	14400

ASTM C-99

Parallel to Rift, Dry (psi)	1110
Parallel to Rift, Wet (psi)	1110

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	2060



GOLD QUARRY
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101