















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Split Face
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	2" - 9" (Full Bed); 2"-9" (Thin Veneer)
	LENGTHS	Random, 8" - 36" (Full Bed); 6" - 20" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Blue-Gray, Grey, Buff
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f Pallet
	NOTES	

ASTM C-97

Water Absorption %	.50
Bulk Specific Gravity	2.79

ASTM C-170

Parallel to Rift, Dry (psi)	21300
Parallel to Rift, Wet (psi)	20300
Perpendicular to Rift, Dry (psi)	29400
Perpendicular to Rift, Wet (psi)	29100

ASTM C-99

Parallel to Rift, Dry (psi)	2040
Parallel to Rift, Wet (psi)	1690

ASTM C-880

Perpendicular to Rift, Dry (psi)	
Perpendicular to Rift, Wet (psi)	



GOLD QUARRY
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101