















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Bedface
	PATTERN	2:1 Sawn Course Heights Dimensional Ashlar
	HEIGHTS	2.25", 5"
	LENGTHS	6" - 20" (Crated or palletized material can exceed 20")
	DEPTHS	Thin Veneer: .75" - 1.25" Full Veneer: 3" - 5"
	COLORS	Mix of Grays, Buff, Beige
	COVERAGE	Full Veneer: 35-40 Sq Ft per Ton
	WEIGHT	~13.7 lbs per Sq Ft (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 200 s/f Pallet
	CORNERS	10 Ln/Ft Box; 100 Ln/Ft Crate; 100 Ln/Ft Pallet
	NOTES	NEW (Same as Fond du Lac Dimensional but with 2 heights: 2.25" & 5")

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101