Fond du Lac Natural stone
BUILDING & LANDSCAPE STONE

Fond du Lac Dimensional Clean Split

SPECIFICATIONS

GEOLOGY	Limestone
TYPE	100% Split Face
PATTERN	2:1 Coursed, or Dimensional Ashlar | Random Ashlar
HEIGHTS	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
LENGTHS	Full Veneer: 8"-48" | Thin Veneer: 6" - 20" (Crated or Palletized material can exceed 20")
DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
COLORS	Cream, Gray-Grey, White
COVERAGE	35-40 Square Feet Per Ton (Full Bed)
WEIGHT	13.7 lbs. per square foot (Thin Veneer)
FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f pallet, 180 s/f pallet
CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet, Crated material can exceed 20"
NOTES	

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730

CERTIFIED GENUINE STONE
GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101

CERTIFIED GENUINE STONE™
GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101

Fond du Lac Natural Stone | fdlnaturalstone.com
N4224 Hwy 175 PO Box 347 Fond du Lac, WI 54936-0347
Phone: 920-923-2800 | Toll Free: 877-923-2800 | Fax: 920-923-3800