















# Fond du Lac Sawn-Face Dimensional



## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	100% Sawn-Face
	<b>PATTERN</b>	2:1 Coursed, or Dimensional Ashlar   Random Ashlar
	<b>HEIGHTS</b>	Full Bed & Thin Veneer: 2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%)
	<b>LENGTHS</b>	Full Bed: 8" - 48"   Thin Veneer: 8"-20" (Crated and Palletized material can exceed 20")
	<b>DEPTHS</b>	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
	<b>COLORS</b>	Cream, Gray-Grey, White
	<b>COVERAGE</b>	35-40 Square Feet Per Ton (Full Bed)
	<b>WEIGHT</b>	14 lbs per square foot (Thin Veneer)
	<b>FLATS</b>	10 s/f Box; 100 Sq/ft Crate, 180 Sq/ft Crate; 100 Sq/ft pallet, 180 Sq/ft pallet
	<b>CORNERS</b>	10 Ln/ft Box; 100 Ln/ft Crate; 100 Ln/ft pallet, Crated material can exceed 20"
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

### ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

### ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

### ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRIER  
ANSI/NSC 373-2013  
C0290908-101



GOLD FABRICATOR  
ANSI/NSC 373-2013  
C0289215-101

