















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Bedface
	PATTERN	Sawn Course Heights 2:1 Random Ashlar
	HEIGHTS	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	LENGTHS	8" - 20" (Thin Veneer, crated/palletized material can exceed 20"); 8" - 48" (Full Bed)
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer
	COLORS	Black, Buff, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f pallet, 180 s/f pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	"Graphite Dimensional" was also known as the legacy NSVI product, " Chadwick ". Some photos may still show the former name.

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730

