















## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	60% Bedface, 40% Split Face
	<b>PATTERN</b>	2:1 Sawn Course Heights   Dimensional Ashlar
	<b>HEIGHTS</b>	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	<b>LENGTHS</b>	8" - 24" (Thin Veneer, crated/palletized material can exceed 20"); 8"-48" (Full Bed)
	<b>DEPTHS</b>	3/4" to 1-1/4"
	<b>COLORS</b>	Brown, Buff, Gray-Grey
	<b>COVERAGE</b>	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	<b>WEIGHT</b>	13.7 lbs. per square foot.
	<b>FLATS</b>	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	<b>CORNERS</b>	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	<b>NOTES</b>	<i>Heritage Dimensional™</i> was also known as the legacy NSVI products, "Cedar Creek", and "Pine Creek". Some photos may still be labeled with the former product names.

### ASTM C-97

Water Absorption %	.50 psi
Bulk Specific Gravity	2.79 psi

### ASTM C-170

Parallel to Rift, Dry	21300 psi
Parallel to Rift, Wet	20300 psi
Perpendicular to Rift, Dry	29400 psi
Perpendicular to Rift, Wet	29100 psi

### ASTM C-99

Parallel to Rift, Dry	2040 psi
Parallel to Rift, Wet	1690 psi

### ASTM C-880

Perpendicular to Rift, Dry	
Perpendicular to Rift, Wet	

