















## SPECIFICATIONS

	<b>GEOLOGY</b>	Sandstone
	<b>TYPE</b>	100% Bedface
	<b>PATTERN</b>	2:1 Natural Coursed Ashlar   or Random Ashlar
	<b>HEIGHTS</b>	2.25 inches, 5 inches, 7.75 inches
	<b>LENGTHS</b>	Thin Veneer Only: 6" - 20" (Crated or Palletized Material can exceed 20")
	<b>DEPTHS</b>	3/4 inch - 1.25 inches
	<b>COLORS</b>	Light to medium grays, buff/tan
	<b>COVERAGE</b>	(Not available in full bed-depth)
	<b>WEIGHT</b>	12 lbs per square foot
	<b>FLATS</b>	10 sq ft per Box   100 sq ft Crate   180 sq ft Crate
	<b>CORNERS</b>	10 In ft per Box   100 In ft per Crate
	<b>NOTES</b>	Tumbled gray and buff sandstone, with dimensionally sawn heights, packaged assuming a 1/2" mortar joint.

### ASTM C-97

Water Absorption %	.12
Bulk Specific Gravity	2.78

### ASTM C-170

Parallel to Rift, Dry (psi)	14214
Parallel to Rift, Wet (psi)	14213
Perpendicular to Rift, Dry (psi)	21814
Perpendicular to Rift, Wet (psi)	21320

### ASTM C-99

Parallel to Rift, Dry (psi)	3046
Parallel to Rift, Wet (psi)	3191

### ASTM C-880

Perpendicular to Rift, Dry (psi)	4351
Perpendicular to Rift, Wet (psi)	4351



GOLD QUARRY  
ANSI/NSC 373-2013  
C0290908-101



GOLD FABRICATOR  
ANSI/NSC 373-2013  
C0289215-101