















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	70% Splitface (Fond du Lac Country), 30% Bedface (Fond du Lac Manor)
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed); 2" - 6" (Thin Veneer)
	LENGTHS	Random, from 8" - 36" (Full Bed); 8" - 24" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	Thin Veneer: 3/4" to 1-1/4"
	COLORS	Buff, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14.9 lbs. per square foot.
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Formerly NSVI's "Arlington"; pre-packaged 70% Splitface (FDL Country), 30% Bedface (FDL Manor)

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi

