















SPECIFICATIONS

	GEOLOGY	Sandstone
	TYPE	100% Splitface
	PATTERN	2:1 Natural Course Heights Random Ashlar
	HEIGHTS	3" - 10"
	LENGTHS	Thin Veneer Only: 6" - 20" (Crated or Palletized Material can exceed 20")
	DEPTHS	Thin Veneer Only: 3/4" - 1 1/4"
	COLORS	Mostly cream to white with some light tan
	COVERAGE	
	WEIGHT	Thin Veneer: ~13 pounds per square foot
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f Pallet
	NOTES	

ASTM C-97

Water Absorption %	1.2
Bulk Specific Gravity	

ASTM C-170

Parallel to Rift, Dry (psi)	15061
Parallel to Rift, Wet (psi)	17103
Perpendicular to Rift, Dry (psi)	
Perpendicular to Rift, Wet (psi)	

ASTM C-99

Parallel to Rift, Dry (psi)	2877
Parallel to Rift, Wet (psi)	2688

ASTM C-880

Perpendicular to Rift, Dry (psi)	2186
Perpendicular to Rift, Wet (psi)	1569



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101