















## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	100% Splitface
	<b>PATTERN</b>	2:1 Random Ashlar
	<b>HEIGHTS</b>	2" - 8"
	<b>LENGTHS</b>	Thin Veneer: 6" - 20" (Crated or palletized material can exceed 20")
	<b>DEPTHS</b>	3/4" to 1-1/4"
	<b>COLORS</b>	Buff, Burnt Orange, Burgundy, Gray-Grey, Lavender
	<b>COVERAGE</b>	
	<b>WEIGHT</b>	14.8 lbs per square foot
	<b>FLATS</b>	10 s/f Box, 100 s/f Crate, 180 s/f Crate
	<b>CORNERS</b>	10 l/f per box; 100 l/f per NTV Crate
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	.6
Bulk Specific Gravity	2.7

### ASTM C-170

Parallel to Rift, Dry (psi)	22163
Parallel to Rift, Wet (psi)	20191
Perpendicular to Rift, Dry (psi)	
Perpendicular to Rift, Wet (psi)	

### ASTM C-99

Parallel to Rift, Dry (psi)	3657
Parallel to Rift, Wet (psi)	1338

### ASTM C-880

Perpendicular to Rift, Dry (psi)	2636
Perpendicular to Rift, Wet (psi)	1084

