















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Coursed Heights; 2:1 Random Ashlar
	HEIGHTS	2" - 8"
	LENGTHS	Thin Veneer: 6" - 20" (Crated or palletized material can exceed 20")
	DEPTHS	Thin Veneer: .75" - 1.25" Full Veneer: 3" - 5"
	COLORS	Muted grays, blues, beige/buff hues.
	COVERAGE	35 - 40 Sq Ft per Ton
	WEIGHT	~13.6 lbs per Sq Ft
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 200 s/f Pallet
	CORNERS	10 Ln Ft per Box; 100 Ln Ft per Crate; 100 Ln Ft per Pallet
	NOTES	NEW (Tumbled "Indigo Country")

ASTM C-97

Water Absorption %	.50
Bulk Specific Gravity	2.79

ASTM C-170

Parallel to Rift, Dry (psi)	21300
Parallel to Rift, Wet (psi)	20300
Perpendicular to Rift, Dry (psi)	29400
Perpendicular to Rift, Wet (psi)	29100

ASTM C-99

Parallel to Rift, Dry (psi)	2040
Parallel to Rift, Wet (psi)	1690

ASTM C-880

Perpendicular to Rift, Dry (psi)	
Perpendicular to Rift, Wet (psi)	



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101