



SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface - Tumbled
	PATTERN	Natural Coursed Height; 2:1 Random Ashlar
	HEIGHTS	Random: 2 inches - 8 inches
	LENGTHS	Thin Veneer: 6 in - 20 in (Crated or pallet-wrapped material can exceed 20 in)
	DEPTHS	Thin Veneer: .75 in - 1.25 in Full Veneer: 3 in - 5 in
	COLORS	Light to medium muted grays, buff, muted blues
	COVERAGE	35 - 40 Sq Ft per Ton
	WEIGHT	~14 lbs per square foot (Thin Veneer)
	FLATS	10 Sq/Ft Box; 100 Sq/Ft Crate, 180 Sq/Ft Crate; 100 Sq/Ft Pallet, 200 Sq/Ft Pallet
	CORNERS	10 Ln Ft per Box; 100 Ln Ft per Crate; 100 Ln Ft per Pallet
	NOTES	NEW:

ASTM C-97

Water Absorption %	.50
Bulk Specific Gravity	2.79

ASTM C-170

Parallel to Rift, Dry (psi)	21300
Parallel to Rift, Wet (psi)	20300
Perpendicular to Rift, Dry (psi)	29400
Perpendicular to Rift, Wet (psi)	29100

ASTM C-99

Parallel to Rift, Dry (psi)	2040
Parallel to Rift, Wet (psi)	1690

ASTM C-880

Perpendicular to Rift, Dry (psi)	
Perpendicular to Rift, Wet (psi)	



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101