















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	3" - 7"
	LENGTHS	Full Veneer: 8" - 36" Thin Veneer: 6" - 20" (Crated or Palletized Material can exceed 20")
	DEPTHS	Thin Veneer: .75" - 1.25" Full Veneer: 3" - 5"
	COLORS	Muted two-toned: Buff/Tan with Gray/Blue Veining
	COVERAGE	35-40 Sq Ft (Full Veneer)
	WEIGHT	~14 lbs per Sq Ft (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 200 s/f Pallet
	CORNERS	10 Ln Ft per Box; 100 Ln Ft per Crate; 100 Ln Ft per Pallet
	NOTES	NEW (Tumbled "Blue Country")

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRY
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101