



SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Splitface
	PATTERN	Natural Coursed Heights 2:1 Random Ashlar
	HEIGHTS	Random, 2" - 8" (Full Bed & Full Veneer)
	LENGTHS	Full Veneer: 8" - 36" Thin Veneer: 6" - 20" (Crated or palletized material can exceed 20 inches.)
	DEPTHS	Thin Veneer: .75 in - 1.25 in Full Veneer: 3 in - 5 in
	COLORS	Soft light to medium gray, muted beige, buff.
	COVERAGE	Full Veneer: 35-40 Sq Ft per Ton.
	WEIGHT	13.6 lbs per sq ft
	FLATS	10 s/f Box, 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 200 s/f Pallet
	CORNERS	10 Ln/Ft per box, 100 Ln Ft per Crate; 100 Ln Ft per Pallet
	NOTES	<i>Pre-packaged tumbled blend: 50% Columbia, 50% Rome</i>

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730